



Super Foam 224 is low- free rise density rigid spray foam that has excellent thermal conductivity, dimensional stability, and adhesion to the ground surface. In addition, generation and form uniformly and continuously followed by good mechanical properties and resistance to water absorption, and by the suitable reactive workability is excellent and can be constructed regardless of the season.

Usage

Internal insulation of factory, general building, housing, gymnasium.
Polyurea insulation coating system.

Application Procedure

Procedure	<ol style="list-style-type: none"> 1. Surface treatment The surface should be cleaned and dried well to avoid sand, cement powder, soil and other contaminants. 2. Weather condition <ol style="list-style-type: none"> 1) Air temperature: 0 ~ 40 °C 2) Surface temperature: 0 ~ 40 °C 3) Relative humidity: 80% or less 4) Wind speed: 15 mph or less (without windshield) 5) The surface temperature should be at least 3 °C above the dew point temperature to prevent condensation. 3. Spray equipment Spray equipment for Polyurea or Urethane foam
Caution for usage	<ol style="list-style-type: none"> 1. Avoid painting on rainy days, high humidity (80% or more) or low temperature (below 0 °C.) 2. The cracks in the base are worked after flattening by repair work such as plugging. 3. Proper primer coating should be applied according to the type of the surface.
Caution for handling	<ol style="list-style-type: none"> 1. Store the product in a dry, cool place at room temperature (5 ~ 35 °C) away from fire and direct sunlight. Keep container tightly closed with the injection port facing upward. 2. Since the product is flammable, store it in a dry, cold cow at room temperature (5 ~ 35 °C) away from direct sunlight. Keep container tightly closed with the injection port facing upward. 3. Dispose of the waste paint through a waste disposal company designated by the Ministry of Environment. 4. Please use this product within the storage period.
Warning	Please refer to the warning in the appendix.
Application system	<ol style="list-style-type: none"> 1. Primer : SUPERDECK 100, SUPERDECK 110 (If necessary) 2. Intermediate 1 : SUPERFOAM series 3. Intermediate 2 : SUPERDECK U,H series (If necessary) 4. Top coat : SUPERDECK 300 (If necessary)

Physical Data

Applied over	Concrete, Steel	Components	2
Cream time (sec, 20°C)	3.5 ± 1.5	Rise time (sec, 20°C)	14 ± 3
Free rise density (Kg/ m³)	24 ± 1	Thermal conductivity (W/m.K)	≤ 0.023
Compressive strength (Kgf/cm²)	1.2 ≥	Mixing ratio	1 : 1 (vol)
Packing Unit	<A>: 250Kg : 230Kg	Shelf Life	6 months (0~15°C) 2 months (20~25°C) 1 months (30~35°C)